

ZP127 – ZINC PHOSPHATE PRIMER

 Compilation date: 24/09/2015
 Revision No: 1

DESCRIPTION	Single component high build anticorrosive alkyd primer for brush application
USES & BENEFITS	<ul style="list-style-type: none"> • First coat for general steelwork, plant and machinery. Also suitable for wood. • High Build • Low odour • Good penetration on bare timber • Fast drying and easily abraded • Good flow characteristics • Multiple coats can be left as a finish coat where a low sheen is required.
PHYSICAL PROPERTIES*	VOC Content : 360g/Ltr Solids % by Weight : 70 Flash Point : >36°C Mixing Ratio : n/a
FINISH	Flat
COLOUR	Limited
COVERAGE	Up to 12m ² /Ltr
PREPARATION	Substrate to be clean, dry and free from grease, rust and millscale. For application to metal substrates, best results are achieved by blast cleaning.
APPLICATION	Brush / Roller : Thin if necessary Ambient temperature : 5-30°C Surface temperature : >3°C above the dew point Clean equipment with SV104 or White spirit
DRYING TIMES	At 20°C Touch dry : 15-30 minutes Recoat : After 24 hours
THINNER	SV104
STORAGE	Keep away from food and drink. Store in original container securely closed and at room temperature (For full text refer to health & safety data sheet)
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.